

**CONVEYOR AND PROCESS BELTS**
**TECHNICAL DATA SHEET**

<b>CODE</b>	<b>NA-129</b>	<b>TYPE</b>	<b>2MT8 S0-S0</b>
-------------	---------------	-------------	-------------------

**COMPOSITION**

<b>Conveying surface</b>	Material	Fabric with silicone impregnation	
	Thickness	--- mm	--- in.
	Surface pattern	Fabric	
	Colour	Natural	
	Coefficient of friction	LF	
<b>Textile carcass</b>	Material	Polyester (PET)	
	Plies no.	2	
	Weft type	Combined	
<b>Driving surface</b>	Material	Fabric with silicone impregnation	
	Thickness	--- mm	--- in.
	Surface pattern	Fabric	
	Colour	Natural	

**TECHNICAL SPECIFICATIONS**

Total thickness	1.20 mm	0.05 in.
Weight	1.10 kg/m <sup>2</sup>	0.22 lbs./sq.ft
Elongation at 1%	8 N/mm	46.0 lbs./in.
Max. admissible pull	16 N/mm	91.0 lbs./in.
Temperature resistance <sup>(1)</sup>	min.	-40 °C -40 °F
	max.	160 °C 320 °F

<sup>(1)</sup> Use of the belt with limit values may reduce its life.

Minimum radius / diameter <sup>(2)</sup>		
■ Knife edge minimum radius	no	
■ Bending roller min. diameter	30 mm	1.18 in.
■ Counter-bending roller min. diameter	40 mm	1.57 in.


<sup>(2)</sup> The above mentioned values depend on the type of CHIORINO joint recommende

Coefficient of friction on driving surface		
■ Raw steel sheet	0.30 [-]	
■ Laminated plastic/wood	0.40 [-]	
■ Steel roller	0.30 [-]	
■ Rubberized roller	0.50 [-]	

Max. production width	2000 mm	79 in.
-----------------------	---------	--------

**SUITABLE FOR**

Packaging


**FEATURES**

Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	yes
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	yes
Curved conveyor	no
Chemical resistances <a href="#">link</a>	10

**COMPLIANCES**

REACH EC 1907/2006 Regulation and Amendments

**NOTES**

Issue: 24-07-2009


Last Update: 23-06-2016

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CODE **NA-129** TYPE **2MT8 S0-S0**

Recommended joining procedure **DOUBLE Z**



A = 50 mm  
B = 12 mm

Other joining methods can be used:  
SKIVED JOINT '1'

Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press **P \ PL \ PLS**


Press settings	
Upper platen temperature	120 °C
Lower platen temperature	120 °C
Temperature gauge setting	120 °C
Curing time in press	12 min.
Pressure	3 bar
Film	none
Cement	KIT SILCOL

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.  
3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



• Notes

Issued: 26-10-2005

Last Update: 30-01-2014

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.