

#### **CONVEYOR AND PROCESS BELTS**

## **TECHNICAL DATA SHEET**

# 2M12 U0-V10 RT FR

#### **NA-60** CODE

**TYPE** 

	COMPOSITION				
Conveying surface	Material	PVC 45 Sh.A (±5)			
	Thickness	1.00 mm <i>0.039 in.</i>			
	Surface pattern	RT			
	Colour	Anthracite			
	Coefficient of friction	HF			
<b>Textile</b> carcass	Material	Polyester (PET)			
	Plies no.	2			
	Weft type	Rigid			
<b>Driving</b> surface	Material	Fabric with polyurethane (TPU) impregnation			
	Thickness	mm <i> in.</i>			
	Surface pattern	LdB fabric			
	Colour	Grey			

TECHNICAL SPECIFICATIONS

Total thickness	2.70 mm	0.11	in.	
Weight	2.90 kg/m <sup>2</sup>	0.59	lbs./sq.ft	
Elongation at 1%	12 N/mm	69.0	lbs./in.	
Max. admissible pull	24 N/mm	137.0	lbs./in.	
Temperature resistance (1)	min.	-10 °C	14	°F
resistance (1)	max.	60 °C	140	°F
(1) Use of the belt with limit values may reduce its life.				

Minimum radius / diameter (2)

■ Knife edge minimum radius no

60 mm 2.36 in. ■ Bending roller min. diameter ■ Counter-bending roller min. diameter 3.15 in. 80 mm

### Coefficient of friction on driving surface


0.20 [-] Raw steel sheet ■ Laminated plastic/wood 0.25 [-] 0.20 [-] ■ Steel roller Rubberized roller 0.30 [-]

2000 mm Max. production width 79 in.

## SUITABLE FOR

Airports

Materials handling



### **FEATURES**

Humidity influence		
Suitable to metal detector		
Permanent antistatic dynamically (UNI EN ISO 21179)	yes	
Static conductivity (UNI EN ISO 284)		
Conveying on skid bed	yes	
Conveying on rollers	yes	
Conveying on skid bed on top and return	no	
Troughed conveying	no	
Swan neck conveying		
Inclined conveying		
Accumulators belts	no	
Curved conveyor	no	
Chemical resistances <u>link</u>		

#### **COMPLIANCES**

REACH EC 1907/2006 Regulation and Amendments

Flame Retardant UNI EN ISO 340 Flame Retardant UL94HB Horizontal Burning

NOTES

Issue: 24-07-2009 Last Update: 23-06-2016

#### **DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

 $<sup>^{(2)}</sup>$  The above mentioned values depend on the type of CHIORINO joint recommends




#### **CONVEYOR AND PROCESS BELTS**

#### **JOINING TECHNICAL DATA SHEET**

CODE NA-60 TYPE **2M12 U0-V10 RT FR** 

SINGLE Z

## Recommended joining procedure



#### Other joining methods can be used:

DIAGONAL SINGLE Z SKIVED JOINT '2' DOUBLE Z STEP


Check our general catalogue to get further info on CHIORINO joining methods.

#### Pressing

## Heating press P\PL\PLS


Press settings			
Upper platen temperature	170 °C		
Lower platen temperature	170 °C		
Temperature gauge setting	170 °C		
Curing time in press	3 min.		
Pressure	3 bar		
Film	none		
Cement			

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
  A periodical inspection of the thermostats is recommended, to make sure they function correctly.

## Layout of components



### Notes

Issued: 10-12-2005 Last Update: 30-01-2014

#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.